

## ADHESIVE DERIVED FROM DIMERIC FATTY ACID OR DIMERIC FATTY DIOL

**Field of Invention**

- 5 The present invention relates to an adhesive comprising an isocyanate, and in particular to the use thereof as a wood adhesive.

**Background**

- 10 Adhesives have been used in the wood industry for many years. Uses include the lumber industry, the aggregated fibre board industry, the medium density fibreboard (MDF) market, and the oriented strand board (OSB) market. The chemical composition of wood adhesives varies greatly, but the most widely used adhesives are based upon phenol formaldehyde, urea formaldehyde, urea-melamine  
15 formaldehyde, and isocyanate such as polymeric diphenyl methane diisocyanate (pMDI).

- pMDI adhesives, in particular, are popular in the USA. pMDI adhesives are normally formed by reacting diphenyl methane diisocyanate with a polyether polyol such as  
20 polypropylene glycol. One of the advantages of pMDI adhesives is that the cure mechanism relies upon the moisture content of the wood reacting with free NCO groups in the adhesive to form polyurea, which differs from the other major adhesives in that for most applications heat and pressure is not required to develop a mechanically acceptable joint. However, one of the limiting factors which prevents  
25 greater use of pMDI adhesives, when compared, for example to phenol formaldehyde based resins, is their performance under wet conditions. An improvement in the hydrolytic stability of pMDI based adhesives, whilst at least maintaining the adhesive property, is required to significantly increase the use thereof.

30 **Summary of the Invention**

We have now surprisingly discovered an isocyanate based adhesive which reduces or substantially overcomes at least one of the aforementioned problems.

Accordingly, the present invention provides an adhesive comprising polyisocyanate and a polyol comprising at least one dimer fatty acid and/or dimer fatty diol.

5 The invention also provides a substrate coated with an adhesive comprising polyisocyanate and a polyol comprising at least one dimer fatty acid and/or dimer fatty diol.

10 The invention further provides the use of an adhesive comprising polyisocyanate and a polyol comprising at least one dimer fatty acid and/or dimer fatty diol, to adhere wood.

15 The invention still further provides wooden joists, wooden frames and/or external wooden cladding adhered together using an adhesive comprising polyisocyanate and a polyol comprising at least one dimer fatty acid and/or dimer fatty diol.

20 The adhesive is preferably formed from, i.e. comprises the reaction product of at least one polyisocyanate. The polyisocyanate component is preferably at least one isocyanate which has a functionality of at least 2, and may be an aliphatic or aromatic isocyanate.

25 An aliphatic isocyanate such as hexamethylene 1,6-diisocyanate may be employed, but an aromatic isocyanate is preferred such as tolylene diisocyanate, m-phenylene diisocyanate, p-phenylene diisocyanate, xylylene diisocyanate, 4,4'-diphenyl methane diisocyanate, 2,4'-diphenyl methane diisocyanate, 2,2'-diphenyl methane diisocyanate, hexamethylene diisocyanate, isophorone diisocyanate, polymethylenepolyphenyl diisocyanate, 3,3'-dimethyl-4,4'-biphenylene diisocyanate, 3,3'-dimethyl-4,4'-diphenylmethane diisocyanate, 3,3'-dichloro-4,4'-biphenylene diisocyanate, 1,5-naphthalene diisocyanate, or modified compounds thereof such as uretonimine-modified compounds thereof. The polyisocyanate monomers can be  
30 used alone or as mixtures thereof. In a preferred embodiment, diphenyl methane diisocyanate (MDI) is used, more preferably 2,4'-diphenyl methane diisocyanate. In a particularly preferred embodiment, 2,4'-diphenyl methane diisocyanate is used as a mixture with 4,4'-diphenyl methane diisocyanate, preferably at a ratio by weight of 0.5 to 2:1, more preferably 0.8 to 1.2:1, and particularly approximately 1:1.

The polyisocyanate preferably has a viscosity at 25°C (measured as described herein) in the range from 1 to 500, more preferably 50 to 400, particularly 100 to 300, and especially 150 to 250 mPa.s.

- 5 The adhesive is preferably formed from, i.e. comprises the reaction product of, at least one polyol. The polyol may comprise polyol, triol, or diol, and preferably diol. The polyol preferably comprises and/or is formed from, i.e. comprises the reaction product of, at least one dimer fatty acid and/or dimer fatty diol and/or equivalent thereof.

10

The term dimer fatty acid is well known in the art and refers to the dimerisation product of mono- or polyunsaturated fatty acids and/or esters thereof. Preferred dimer fatty acids are dimers of C<sub>10</sub> to C<sub>30</sub>, more preferably C<sub>12</sub> to C<sub>24</sub>, particularly C<sub>14</sub> to C<sub>22</sub>, and especially C<sub>18</sub> alkyl chains. Suitable dimer fatty acids include the dimerisation products of oleic acid, linoleic acid, linolenic acid, palmitoleic acid, and elaidic acid. The dimerisation products of the unsaturated fatty acid mixtures obtained in the hydrolysis of natural fats and oils, e.g. sunflower oil, soybean oil, olive oil, rapeseed oil, cottonseed oil and tall oil, may also be used. Hydrogenated, for example by using a nickel catalyst, dimer fatty acids may also be employed.

20

In addition to the dimer fatty acids, dimerisation usually results in varying amounts of oligomeric fatty acids (so-called "trimer") and residues of monomeric fatty acids (so-called "monomer"), or esters thereof, being present. The amount of monomer can, for example, be reduced by distillation. Particularly preferred dimer fatty acids, used in the present invention, have a dicarboxylic (or dimer) content of greater than 45%, more preferably greater than 60%, particularly greater than 70%, and especially greater than 75% by weight. The trimer content is preferably less than 55%, more preferably in the range from 5 to 40%, particularly 10 to 30%, and especially 15 to 25% by weight. The monomer content is preferably less than 10%, more preferably in the range from 0.5 to 5%, particularly 1 to 4%, and especially 2 to 3% by weight.

30

Dimer fatty diols can be produced by hydrogenation of the corresponding dimer fatty acid. The same preferences above for the dimer fatty acid apply to the corresponding dimer fatty diol component of the polyol.

35

The polyol component of the adhesive preferably comprises an oligomer or polymer (hereinafter referred to as a polymer) formed from, i.e. comprises the reaction product of, at least one dimer fatty acid and/or dimer fatty diol and/or equivalent thereof. Suitable polymers are polyesters, including homopolymers, and random or block co- and ter-polymers thereof. The optional non-ester component includes amides and urethanes. Polyesteramides are preferred copolymers. Alternatively blends, preferably of polyester and polyamide and/or polyurethane, may be employed.

The molecular weight (number average) of the polyol is preferably in the range from 500 to 5,000, more preferably 600 to 4,000, particularly 700 to 3,000, and especially 800 to 2,000.

In a preferred embodiment of the present invention, the polyol comprises an oligoester or polyester (hereinafter referred to as a polyester). Polyester is normally produced in a condensation reaction between at least one polycarboxylic acid and at least one polyol. Dicarboxylic acids and diols are preferred. The preferred dicarboxylic acid component of the polyester used in the present invention comprises at least one dimer fatty acid, as described above.

The dicarboxylic acid component of the polyester may also comprise non-dimeric fatty acids. The non-dimeric fatty acids may be aliphatic or aromatic, and include dicarboxylic acids and the esters, preferably alkyl esters, thereof, preferably linear dicarboxylic acids having terminal carboxyl groups having a carbon chain in the range from 2 to 20, more preferably 6 to 12 carbon atoms, such as adipic acid, glutaric acid, succinic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, heptane dicarboxylic acid, octane dicarboxylic acid, nonane dicarboxylic acid, decane dicarboxylic acid, undecane dicarboxylic acid, dodecane dicarboxylic acid and higher homologs thereof. Adipic acid is a particularly preferred non-dimeric fatty acid.

A monomeric dicarboxylic acid anhydride, such as phthalic anhydride, may also be employed as the or as part of the non-dimeric fatty acid component.

The polyester is preferably formed from dimer fatty acids to non-dimer fatty acids present at a ratio in the range from 60 to 100%:0 to 40%, more preferably 70 to

100%:0 to 30%, particularly 80 to 100%:0 to 20%, and especially 90 to 100%:0 to 10% by weight of the total dicarboxylic acids. In a particularly preferred embodiment of the present invention the dicarboxylic acid component of the polyester is substantially all dimer fatty acid.

5

The polyol component of the polyester is suitably of low molecular weight, preferably in the range from 50 to 650, more preferably 60 to 150, and particularly 60 to 100.

10

The polyol component may comprise polyols such as pentaerythritol, triols such as glycerol and trimethylolpropane, and preferably diols. Suitable diols include straight chain aliphatic diols such as ethylene glycol, diethylene glycol, 1,3-propylene glycol, dipropylene glycol, 1,4-butylene glycol, 1,6-hexylene glycol, branched diols such as neopentyl glycol, 3-methyl pentane glycol, 1,2-propylene glycol, and cyclic diols such as 1,4-bis(hydroxymethyl)cyclohexane and (1,4-cyclohexane-dimethanol). Ethylene glycol and propylene glycol are preferred diols.

15

The polyol component of the polyester may also comprise a dimer fatty diol as described above. The same preferences above for the dimer fatty acid apply to the corresponding dimer fatty diol component of the polyester.

20

The polyester preferably comprises the reaction residues of diol and dicarboxylic acid present at a molar ratio in the range from 1 to 5:1, more preferably 1.1 to 3:1, particularly 1.15 to 2:1, and especially 1.2 to 1.5:1. The diol is preferably present in sufficient molar excess that the polyester is terminated at both ends with hydroxyl groups.

25

In a preferred embodiment, the polyester is formed from dimer fatty acid and at least one diol selected from ethylene glycol and propylene glycol.

30

The polyester preferably comprises on average in the range from 1 to 5, more preferably 1.5 to 4, particularly 2 to 3.5, and especially 2.5 to 3 ester bonds.

The polyester preferably has a molecular weight (number average) in the range from 750 to 4,000, more preferably 800 to 2,500, particularly 850 to 1,500, and especially 900 to 1,200.

35

The polyester preferably has a glass transition temperature ( $T_g$ ) in the range from -55 to 0°C, more preferably -50 to -20°C, particularly -45 to -25°C, and especially -40 to -30°C.

- 5 The polyester preferably has a hydroxyl value (measured as described herein) in the range from 40 to 220, more preferably 52 to 150, particularly 75 to 140, and especially 100 to 125 mgKOH/g. In addition, the polyester preferably an acid value (measured as described herein) of less than 1, more preferably less than 0.5, and particularly less than 0.3 mgKOH/g.

10

The polyester preferably has a viscosity at 25°C (measured as described herein) in the range from 600 to 2,000, more preferably 700 to 1,500, particularly 750 to 1,200, and especially 800 to 1,000 mPa.s.

- 15 The polyol, preferably polyester, preferably comprises in the range from 10 to 100%, more preferably 25 to 75%, particularly 35 to 60%, and especially 40 to 50% by weight of reaction residues of dimer fatty acid and/or dimer fatty diol and/or equivalent thereof.

- 20 In one embodiment of the invention, at least one of the aforementioned polyisocyanates is reacted with at least one of the aforementioned polyesters, to form an adhesive resin.

- 25 The ratio of polyisocyanate to polyester starting materials which are mixed together to react to form the adhesive is preferably in the range from 20 to 80%:20 to 80%, more preferably 35 to 75%:25 to 65%, particularly 50 to 70%:30 to 50%, and especially 60 to 70%:30 to 40% by weight. The polyisocyanate is preferably used in molar excess relative to OH group content of the polyester, so as to obtain an adhesive composition comprising an isocyanate-terminated polyester and unreacted
- 30 isocyanate.

The NCO:OH molar ratio of the mixture of the polyisocyanate and polyester starting materials is preferably in the range from 1.1 to 16:1, more preferably 2 to 14:1, particularly 3 to 12:1, and especially 6 to 10:1.

35

A catalyst may be, and preferably is, employed in the reaction to produce an adhesive according to the present invention. Examples of suitable urethane catalysts include tertiary amines such as triethylamine, 1,4-diazabicyclo[2.2.2.]octane (DABCO), N-methylmorpholine, N-ethylmorpholine, N,N,N',N'-

5 tetramethylhexamethylenediamine, 1,2-dimethylimidazol; and tin compounds such as tin(II)acetate, tin(II)octanoate, tin(II)laurate, dibutyltin dilaurate, dibutyltin dimaleate, dioctyltin diacetate and dibutyltin dichloride. The catalyst may be used alone or as mixtures thereof.

10 The adhesive preferably has a molecular weight (number average) in the range from 600 to 2,000, more preferably 650 to 1,500, particularly 700 to 1,000, and especially 750 to 850. The molecular weight of the adhesive composition is relatively low due to the presence of significant residual amounts of unreacted polyisocyanate which reduces the average molecular weight thereof.

15 The adhesive is preferably formed from, i.e. comprises the reaction product of, on average in the range from 1 to 6, more preferably 2 to 5, particularly 2.5 to 4.5, and especially 3 to 4 polyisocyanate monomers, and also blocks of polymer, preferably polyester.

20 The adhesive preferably has an isocyanate content (measured as described herein) in the range from 10 to 40%, more preferably 12 to 30%, particularly 14 to 25%, and especially 16 to 20% NCO.

25 The adhesive preferably comprises in the range from 2 to 60%, more preferably 8 to 40%, particularly 14 to 30%, and especially 16 to 20% by weight of reaction residues of dimer fatty acid and/or dimer fatty diol and/or equivalent thereof.

30 The adhesive preferably has a viscosity at 23°C (measured as described herein) in the range from 2 to 40, more preferably 3 to 30, particularly 4 to 20, and especially 5 to 10 Pa.s.

35 The adhesive may also comprise other optional components such as fillers, for example nylon, glass fibre, fumed silica, wood flour; and other agents such as pigments, antioxidants, stabilizers, flow additives etc.

The adhesive is preferably applied to a suitable substrate, preferably wood, in situ as a free flowing viscous solid, and cured, by reacting with water present in the substrate, at ambient temperature.

- 5 A particularly surprising feature of the adhesive according to the present invention is increased penetration thereof into wood compared to prior art adhesives, which can result in improved adhesive properties.

10 The cured adhesive preferably has a lap shear adhesion value (measured as described herein) of greater than 6, more preferably greater than 8, particularly greater than 10, and especially greater than 12 MPa.

15 The cured adhesive preferably has a creep rupture adhesion value in air at ambient temperature (23°C) (measured as described herein) at a stress value of 8 MPa and/or 6 MPa and/or 4 MPa of greater than 500,000, and more preferably greater than 1,000,000 seconds.

20 The cured adhesive suitably has a creep rupture adhesion value in water at ambient temperature (23°C), and more suitably in water at elevated temperature (90°C) (measured as described herein) (i) at a stress value of 8 MPa of greater than 50, preferably greater than 100, more preferably greater than 500, particularly greater than 1,000, and especially greater than 1,500 seconds, and/or (ii) at a stress value of 6 MPa of greater than 150, preferably greater than 500, more preferably greater than 2,500, particularly greater than 10,000, and especially greater than 15,000 seconds, and/or (iii) at a stress value of 4 MPa of greater than 2,000, preferably greater than 10,000, more preferably greater than 100,000, particularly greater than 500,000, and especially greater than 1,000,000 seconds.

30 A particular surprising feature of an adhesive according to the present invention is that the adhesion values are effectively maintained under hot moist conditions. Thus, the time to failure of the adhesive in the creep rupture adhesion test described herein at 90°C in water at a stress value of 4 MPa, preferably 6 MPa, and more preferably 8 MPa, is preferably at least 50%, more preferably at least 70%, particularly at least 90%, and especially 100% or greater of the value obtained when tested at 23°C in air.

35



The adhesive described herein is suitable for use on wood, including soft, hard and tropical woods. Particularly preferred woods include yellow birch, ponderosa pine, and especially tropical hard woods such as bengkirai (or balau). The adhesive is particularly suitable for external use. The adhesive can be used, for example, in wooden joists, wooden frames and external wooden cladding.

The adhesive may also be used on materials other than wood, for example on textiles, plastics, and metals such as steel, copper and aluminium. Suitable applications include panel lamination, automotive, furniture and general assembly.

In this specification the following test methods have been employed:

(i) Molecular weight number average was determined by Gel Permeation Chromatography (GPC).

(ii) The softening point and glass transition temperature ( $T_g$ ) were measured by Differential Scanning Calorimetry (DSC) at a scan rate of 20°C/minute using a Mettler DSC30.

(iii) The hydroxyl value is defined as the number of mg of potassium hydroxide equivalent to the hydroxyl content of 1 g of sample, and was measured by acetylation followed by hydrolysis of excess acetic anhydride. The acetic acid formed was subsequently titrated with an ethanolic potassium hydroxide solution.

(iv) The acid value is defined as the number of mg of potassium hydroxide required to neutralise the free fatty acids in 1 g of sample, and was measured by direct titration with a standard potassium hydroxide solution.

(v) (a) Viscosity of the polyisocyanate and polyester were measured 25°C using a Brookfield Reometer.

(b) Viscosity of the adhesive was measured using a Rheometrics rheometer. A sample of the adhesive was placed between two spherical platens of 12.5 cm diameter. A frequency of 10 radians per second was used as well as a 10% strain.

The Complex Viscosity ( $\eta^*$ ) was measured at ambient temperature (23°C).

(vi) Lap shear adhesion was measured using yellow birch (US hardwood). The wood was conditioned in a temperature/humidity controlled oven to have a moisture content of 12 weight % at 23°C. This was measured using a dedicated wood moisture meter (mini-Ligno XL moisture meter) calibrated for yellow birch. The lap shear specimen comprised 2 halves (25 mm x 160 mm x 4 mm). The 2 halves were stuck together to

form a lapped joint which overlapped by 25 mm. The adhesive was applied and a joint of adhesive thickness of less than 0.5 mm was achieved. These test specimens were clamped together to protect the joint, and left to cure in a controlled laboratory atmosphere of 23°C and 50% relative humidity. The adhesive joints were then tested to destruction for specimens cured for 7 days after preparation. The wood grain was oriented in the tensile direction. The Lap shear tests were carried out according to ASTM D-1002/99 lap-shear adhesion test.

(vii) Creep rupture adhesion was measured using yellow birch. Samples were prepared by matching the wood samples to comprise 2 halves (40 mm x 20 mm x 4 mm). The wood was oriented so that the wood grain was in the stress direction. These samples were further machined using a finger jointing tool (as described in ASTM D5572). These finger joints were made with a 5 mm interlocking section. This type of joint provides some stability during manufacture of the adhesive joint, and gives a larger area of adhesive exposed to the aggressive conditions of the test. The resultant sample was 75 mm x 20 mm x 4 mm. The creep rupture tests were carried out using a lever loaded creep rupture apparatus. The above samples were clamped into tensile grips and a weight applied. This arrangement was used to tension the sample, and the general principle applied whereby the sample was loaded and the time taken for the specimen to fail was recorded electronically from time switches. This approach was used when testing at ambient (23°C), or elevated temperature (90°C), in air or water environments. The methodology is that initially a large tensile force was applied, which gives an instant failure. The force was then reduced by an agreed increment, and the time to failure was increased. This principle was applied until the time to failure increased until failures were not seen over a 6 week timespan. This data was then plotted as a stress versus log time to failure plot. The time for failure in seconds at stress values of 8, 6, and 4 MPa were then read off the graph.

The invention is illustrated by the following non-limiting examples.

#### Example 1

##### (i) Synthesis of Polyol

2210 g of "Pripol" 1017 ((trade mark) dimer acid, C36 dicarboxylic (ex Uniqema)) and 957 g ethylene glycol were reacted in a 4 litre standard distillation unit including separation column at approximately 190°C for 5.9 hours at atmospheric pressure.

The heating time was 3.9 hours, and the maximum temperature of the distillation

column was 105°C. After a reaction time of 0.3 hour, 0.26 ml of 0.01 weight % solution of tetra butyl titanate was added. When the reaction mixture reached an acid value of 0.36 mg KOH/g, the excess ethylene glycol was distilled off at a maximum distillation column temperature of 150°C, and a minimum pressure of 2.3 mbar. The resultant oligoester was obtained by filtering at 85°C, and exhibited the following properties, measured as described herein.

(i) The hydroxyl value was 117 mgKOH/g.

(ii) The acid value was 0.28 mgKOH/g.

#### (i) Synthesis of Adhesive

100 g of the oligoester produced above was placed into a 500 ml round bottomed flask fitted with a mechanical stirrer, nitrogen inlet, thermocouple, dropping funnel and vacuum take-off line. The oligoester was heated to 120°C and a vacuum was applied down to 25 mbar, to remove any water from the oligoester. The vacuum was held for 1 hour, and then released by allowing nitrogen into the reactor. The reaction was then cooled to 80°C and 174 g of liquid VKS20 (MDI (ex Bayer)) was added over a period of 10 minutes from a dropping funnel. The dropping funnel was removed and replaced with a drying tube. The reaction then continued for 2 hours at 80°C, after which time the resin was poured into two glass bottles, flushed with dry nitrogen and sealed. The resulting adhesive had the following properties, measured as described herein;

(i) Lap shear adhesion value was 8 MPa.

(ii) Creep rupture adhesion value at 23°C in air was >1,000,000 seconds at a stress of 8 MPa.

(iii) Creep rupture adhesion value in water at 90°C was;

a) 2700 seconds at a stress of 8 MPa,

b) 15,350 seconds at a stress of 6 MPa, and

c) >1,000,000 seconds at a stress of 4 MPa.

#### Example 2

This is a comparative example not according to the present invention. The procedure of Example 1 was repeated except that 100 g of polypropylene glycol of molecular weight number average 1000 was used as the polyol instead of the oligoester, and

reacted with 158.2 g of VKS20. The resulting adhesive had the following properties, measured as described herein;

(i) Lap shear adhesion value was 7 MPa.

5 (ii) Creep rupture adhesion value at 23°C in air was >1,000,000 seconds at a stress of 8 MPa.

(iii) Creep rupture adhesion value at 90°C in water was;

a) 30 seconds at a stress of 8 MPa,

b) 135 seconds at a stress of 6 MPa, and

10 c) 1920 seconds at a stress of 4 MPa.

The above examples illustrate the improved properties of an adhesive according to the present invention.

15

20

25

30

**CLAIMS**

1. An adhesive comprising polyisocyanate and a polyol comprising at least one dimer fatty acid and/or dimer fatty diol.
2. An adhesive according to claim 1 wherein the polyisocyanate has a viscosity in the range from 100 to 300 mPa.s.
3. An adhesive according to either one of claims 1 and 2 wherein the dimer is formed from C<sub>14</sub> to C<sub>22</sub> alkyl chains.
4. An adhesive according to any one of the preceding claims wherein the dimer comprises in the range from 10 to 30% by weight of trimer.
5. An adhesive according to any one of the preceding claims wherein the polyol comprises a polyester.
6. An adhesive according to claim 5 wherein the dicarboxylic acid component of the polyester is substantially all dimer fatty acid.
7. An adhesive according to either one of claims 5 and 6 wherein the diol component of the polyester comprises ethylene glycol and/or propylene glycol.
8. An adhesive according to any one of claims 5 to 7 wherein the molar ratio of the diol and dicarboxylic acid present in the polyester is in the range from 1.15 to 2:1.
9. An adhesive according to any one of claims 5 to 8 wherein the molecular weight of the polyester is in the range from 800 to 2,500.
10. An adhesive according to any one of claims 5 to 9 wherein the glass transition temperature (T<sub>g</sub>) of the polyester is in the range from -50 to -20°C.
11. An adhesive according to any one of the preceding claims having a molecular weight in the range from 650 to 1,500.

12. An adhesive according to any one of the preceding claims having an isocyanate content in the range from 12 to 30% NCO.

13. An adhesive according to any one of the preceding claims comprising in the range from 14 to 30% by weight of dimer fatty acid and/or dimer fatty diol.

14. An adhesive according to any one of the preceding claims having a lap shear adhesion value of greater than 6 MPa.

15. An adhesive according to any one of the preceding claims having a creep rupture adhesion value at a stress value of 8 MPa of greater than 1,000,000 seconds in air at 23°C.

16. An adhesive according to any one of the preceding claims having a creep rupture adhesion value at a stress value of 6 MPa of greater than 2,500 seconds in water at 90°C.

17. An adhesive according to any one of the preceding claims having a creep rupture adhesion value at a stress value of 4 MPa of greater than 500,000 seconds in water at 90°C.

18. An adhesive according to any one of claims 16 to 17 wherein the creep rupture adhesion value in water at 90°C is at least 70% of the value in air at 23°C.

19. An adhesive according claim 18 wherein the creep rupture adhesion value in water at 90°C is at least 90% of the value in air at 23°C.

20. A substrate coated with an adhesive as defined in any one of the preceding claims.

21. The use of an adhesive as defined in any one of claims 1 to 19, to adhere wood.

22. Wooden joists, wooden frames and/or external wooden cladding adhered together using an adhesive as defined in any one of claims 1 to 19.

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 05623

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/36 C08G18/42 C09J175/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 933 232 A (TROUT KENNETH G ET AL) 12 June 1990 (1990-06-12) example 1	1-22
X	WO 01 25307 A (ANGERMUELLER HARALD ; WEGNER EGON (DE); BASF COATINGS AG (DE); SCHW) 12 April 2001 (2001-04-12) example 1 page 1, line 5 - line 11	1-22
X	WO 02 092662 A (CARTER JEFFREY THOMAS ; ICI PLC (GB); APPLEMAN ERIC (NL); UNICHEMA) 21 November 2002 (2002-11-21) example 2 page 1, line 12	1-22
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*G\* document member of the same patent family

Date of the actual completion of the international search

1 April 2004

Date of mailing of the international search report

13/04/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Müller, M

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 05623

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>WO 93 24551 A (PEARS DAVID ALAN ;GOOS  HENDRICUS CORNELIS (NL); JANSSE PETRUS  LEON) 9 December 1993 (1993-12-09)  page 1, line 11 - line 12  page 2, line 7 - line 11  page 4, line 1 - line 2  examples 1-4,6-8</p> <p>-----</p>	1-22



# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. application No

PCT/GB/05623

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4933232	A	12-06-1990	US 4772442 A	20-09-1988
			EP 0269869 A2	08-06-1988
			FI 875079 A	29-05-1988
			NZ 222293 A	27-09-1989
WO 0125307	A	12-04-2001	DE 19948004 A1	12-07-2001
			AU 7914900 A	10-05-2001
			BR 0014603 A	11-06-2002
			CA 2388518 A1	12-04-2001
			WO 0125307 A1	12-04-2001
			EP 1218434 A1	03-07-2002
			JP 2003511498 T	25-03-2003
			US 6632915 B1	14-10-2003
WO 02092662	A	21-11-2002	EP 1397415 A1	17-03-2004
			WO 02092662 A1	21-11-2002
WO 9324551	A	09-12-1993	AU 4316893 A	30-12-1993
			BR 9306496 A	15-09-1998
			CA 2136620 A1	09-12-1993
			DE 69319731 D1	20-08-1998
			DE 69319731 T2	19-11-1998
			WO 9324551 A1	09-12-1993
			EP 0643734 A1	22-03-1995
			ES 2118239 T3	16-09-1998
			JP 3325023 B2	17-09-2002
			JP 7507086 T	03-08-1995
			SG 44644 A1	19-12-1997